



No Minimum Order Quantity
No Lead Times to Ship

COPEPlus™ FR MB 52 PBT

COPEPlus™ FR MB 52 PBT is highly loaded, heat stabilized brominated FR Masterbatch based on flexible engineering grade copolyester elastomer allowing it to be used in all grades of Hytrel®, Arnitel® and Keyflex® with durometer over Shore 40D.

Thermal properties:	Value	Test Method
Melting Temperature @ Peak	193-200 ⁰ C	ISO 11357-1/-3
Other properties:	Value	Test Method
Density	2.05+/-0.05	ISO 1183

Delivery form: pellets

Packaging: 50 lbs. Al/foiled bags

Processing: Designed to be added to grades of Hytrel® and Keyflex using gravimetric feeders during molding, extrusion.

COPEPlus™ FR MB 52 PBT does not required drying if used right from the sealed bags, otherwise drying is necessary. Recommended drying conditions: 100⁰C for 3 hours. Desired moisture content <0.08%